



**WEAR-RESISTANT LIPSTICK WITH JOJOBA GLAZE® – HV**

This lipstick applies easily and has a good skin-feel with excellent wear. The **JOJOBA GLAZE®** improves pigment dispersion, adds moisturizing characteristics, and imparts a noticeable bright shine to the lips.

<b>INCI NAME</b>	<b>TRADE NAME</b>	<b>WT.%</b>
<b>Phase A</b>		
<b>Simmondsia Chinensis (Jojoba) Seed Oil (and)</b>	<b>JOJOBA GLAZE® – HV <sup>1</sup></b>	<b>16.00</b>
<b>Ethylene/Propylene/Styrene Copolymer (and)</b>		
<b>Butylene/Ethylene/Styrene Copolymer</b>		
<b>Simmondsia Chinensis (Jojoba) Seed Oil</b>	<b>Jojoba Oil Golden <sup>1</sup></b>	<b>39.20</b>
<b>Hydrogenated Jojoba Oil</b>	<b>Jojoba Wax Flakes <sup>1</sup></b>	<b>1.60</b>
Ozokerite	Ozokerite SP1021P <sup>2</sup>	2.40
Beeswax	White Beeswax SP422P <sup>2</sup>	2.40
Copernicia Cerifera(Carnauba) Wax	Carnauba SP63 <sup>2</sup>	3.20
Euphorbia Cerifera (Candelilla) Wax	Candelilla SP75 <sup>2</sup>	7.20
Polyglyceryl-3 Diisostearate	Prisorine 3700 <sup>3</sup>	8.00
<b>Phase B</b>		
<b>Simmondsia Chinensis (Jojoba) Seed Oil (and)</b>	<b>JOJOBA GLAZE® – LV <sup>1</sup></b>	<b>11.00</b>
<b>Ethylene/Propylene/Styrene Copolymer (and)</b>		
<b>Butylene/Ethylene/Styrene Copolymer</b>		
D&C Red 7 Calcium Lake	C19-011 D&C Red 7 Ca Lake <sup>4</sup>	2.00
D&C Red 6 Barium Lake	C19-012 D&C Red 6 Ba Lake <sup>4</sup>	3.60
Iron Oxides	C33-134 Black <sup>4</sup>	0.80
Titanium Dioxide	C47-056 Titanium Dioxide <sup>4</sup>	2.60
		100.00

**Procedure**

Heat Phase A to 85-90° C with stirring until the solids are melted. Add dry ingredients of Phase B in increments to JOJOBA GLAZE LV of Phase B. Pass through 3 roll mill. Add Phase B to Phase A and mix until homogeneous. Pour into molds at 85° C and cool.

**Suppliers**

- <sup>1</sup> Desert Whale Jojoba Co.
- <sup>2</sup> Strahl & Pitsch
- <sup>3</sup> Uniqema
- <sup>4</sup> Sun Chemical

**~ DISPERSION ~ GLOSS ENHANCING ~ MOISTURIZING ~ SUSPENSION ~ VISCOSITY BOOSTING ~**

JOJOBA GLAZE® is a registered trademark of Desert Whale Jojoba Company, Inc.

This information is based on our present state of knowledge. No warranty is expressed or implied as to the use or application of this product. The suitability and safety of the final formulation should be confirmed in all respects by appropriate evaluation.